

**DESCRIPTION**

Total thickness	EN 428	mm	3.30
	ASTM F386-02	inch	0.13
Wearlayer thickness	EN 429	mm	1.17
	ASTM F410-02	inch	0.046
Weight	EN 430	g/sq.m	3260
Width of sheet	EN 426	cm	200
	-	feet - inch	6'6"
Length of sheet	EN 426	lm	25
	-	feet - inch	82'
Coverage / roll	-	sq.ft	538.2
	-	sq.m	50




**CLASSIFICATION**

Norm / Product specification	-	-	EN 651
	ASTM F1303-04	-	Type I Grade 1
European classification	EN 685	class	34 - 42
Fire rating	EN 13 501-1	class	C <sub>fl</sub> -s1
	ASTM E648-08	class	Class I
	CAN/ULC S102.2	-	-
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	DIN 51 130	class	R10

**PERFORMANCE**

Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0
Wear group	EN 651	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation (exigency)	EN 433	mm	≤ 0.20
Residual indentation (measure)	-	mm	0.10
Impact sound insulation	EN ISO 717-2	dB	16
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	Protecsol®
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100

**CE MARKING**

	EN 14041	-	
		-	

**TARALAY PREMIUM COMFORT** is a multilayered calendered and pressed acoustic PVC floorcovering available in 2m wide sheet (Group T wear rating).

The product comprises a  $\geq 1$ mm thick, pure, PVC wearlayer incorporating very densely pressed coloured chips, and a Very High Density (**VHD**) foam (yielding a 16 dB sound insulation rating) reinforced with a glass fibre grid.

**TARALAY PREMIUM COMFORT**'s calendered wearlayer is treated with **Protecsol**<sup>®</sup>, a UV cured anti-glazing surface treatment to facilitate easy maintenance and permanently eliminates the need for acrylic emulsion (metallisation). The product is antistatic (AS class 1) and incorporates **Sanosol**<sup>®</sup>, an anti-bacterial and fungicidal treatment.